

TRANSMITTAL LETTER TO THE UNITED STATES
DESIGNATED/ELECTED OFFICE (DO/EO/US)
CONCERNING A FILING UNDER 35 U.S.C. 371

MR2799-3

U.S. APPLICATION NO. (If known, see 37 CFR 1.5)

09/744172

INTERNATIONAL APPLICATION NO.

INTERNATIONAL FILING DATE

PRIORITY DATE CLAIMED

PCT/US00/09816

24 May 2000

24 May 1999

TITLE OF INVENTION PATTERNED SURFACE CLEANING SYSTEM OF MINATURE STRUCTURES

APPLICANT(S) FOR DO/EO/US

Michael T. Duignan

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:

1. ☒ This is a **FIRST** submission of items concerning a filing under 35 U.S.C. 371.
2. ☐ This is a **SECOND** or **SUBSEQUENT** submission of items concerning a filing under 35 U.S.C. 371.
3. ☒ This is an express request to begin national examination procedures (35 U.S.C. 371(f)). The submission must include items (5), (6), (9) and (21) indicated below.
4. ☐ The US has been elected by the expiration of 19 months from the priority date (Article 31).
5. ☒ A copy of the International Application as filed (35 U.S.C. 371(c)(2))
- a. ☐ is attached hereto (required only if not communicated by the International Bureau).
- b. ☐ has been communicated by the International Bureau.
- c. ☒ is not required, as the application was filed in the United States Receiving Office (RO/US).
6. ☐ An English language translation of the International Application as filed (35 U.S.C. 371(c)(2)).
- a. ☐ is attached hereto.
- b. ☐ has been previously submitted under 35 U.S.C. 154(d)(4).
7. ☒ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3))
- a. ☐ are attached hereto (required only if not communicated by the International Bureau).
- b. ☐ have been communicated by the International Bureau.
- c. ☐ have not been made; however, the time limit for making such amendments has NOT expired.
- d. ☒ have not been made and will not be made.
8. ☐ An English language translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371 (c)(3)).
9. ☒ An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)).
10. ☐ An English language translation of the annexes of the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)).

Items 11 to 20 below concern document(s) or information included:

1. ☐ An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
2. ☒ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
3. ☐ A **FIRST** preliminary amendment.
4. ☐ A **SECOND** or **SUBSEQUENT** preliminary amendment.
5. ☐ A substitute specification.
6. ☐ A change of power of attorney and/or address letter.
7. ☐ A computer-readable form of the sequence listing in accordance with PCT Rule 13ter.2 and 35 U.S.C. 1.821 - 1.825.
8. ☐ A second copy of the published international application under 35 U.S.C. 154(d)(4).
9. ☐ A second copy of the English language translation of the international application under 35 U.S.C. 154(d)(4).
10. ☐ Other items or information:

09/744172

PCT/US00/09816

21. ☒ The following fees are submitted:**BASIC NATIONAL FEE (37 CFR 1.492 (a) (1) - (5)):**

Neither international preliminary examination fee (37 CFR 1.482)

nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO

and International Search Report not prepared by the EPO or JPO. \$1000.00

International preliminary examination fee (37 CFR 1.482) not paid to

USPTO but International Search Report prepared by the EPO or JPO \$860.00

International preliminary examination fee (37 CFR 1.482) not paid to USPTO

but international search fee (37 CFR 1.445(a)(2)) paid to USPTO \$710.00

International preliminary examination fee (37 CFR 1.482) paid to USPTO

but all claims did not satisfy provisions of PCT Article 33(1)-(4) \$690.00

International preliminary examination fee (37 CFR 1.482) paid to USPTO

and all claims satisfied provisions of PCT Article 33(1)-(4) \$100.00

ENTER APPROPRIATE BASIC FEE AMOUNT =**CALCULATIONS PTO USE ONLY**

\$ 690.00

Surcharge of \$130.00 for furnishing the oath or declaration later than ☐ 20 ☐ 30
months from the earliest claimed priority date (37 CFR 1.492(e)).

\$

CLAIMS

NUMBER FILED

NUMBER EXTRA

RATE

\$

Total claims

33 - 20 =

13

x \$18.00

\$ 234.00

Independent claims

3 - 3 =

0

x \$80.00

\$

-

MULTIPLE DEPENDENT CLAIM(S) (if applicable)

+ \$270.00

\$

-

TOTAL OF ABOVE CALCULATIONS =

\$ 924.00

☒ Applicant claims small entity status. See 37 CFR 1.27. The fees indicated above
are reduced by 1/2.

\$ 462.00

+

SUBTOTAL =

\$ 462.00

Processing fee of \$130.00 for furnishing the English translation later than ☐ 20 ☐ 30
months from the earliest claimed priority date (37 CFR 1.492(f)).

\$

TOTAL NATIONAL FEE =

\$ 462.00

Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be
accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31). \$40.00 per property +

\$ 40.0

TOTAL FEES ENCLOSED =

\$ 502.00

Amount to be
refunded:

\$

charged:

\$

a. ☒ A check in the amount of \$ 502.00 to cover the above fees is enclosed.b. ☐ Please charge my Deposit Account No. _____ in the amount of \$ _____ to cover the above fees.
A duplicate copy of this sheet is enclosed.c. ☒ The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any
overpayment to Deposit Account No. 18-2011. A duplicate copy of this sheet is enclosed.d. ☐ Fees are to be charged to a credit card. **WARNING:** Information on this form may become public. **Credit card**
information should not be included on this form. Provide credit card information and authorization on PTO-2038.**NOTE:** Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR
1.137 (a) or (b)) must be filed and granted to restore the application to pending status.

SEND ALL CORRESPONDENCE TO:

Morton J. Rosenberg

Rosenberg, Klein & Lee

3458 Ellicott Center Drive, Suite 101

Ellicott City, MD 21043

SIGNATURE

Morton J. Rosenberg

NAME

26,049

REGISTRATION NUMBER



04586

PATTERNED SURFACE CLEANING SYSTEM OF MINIATURE STRUCTURESREFERENCE TO RELATED APPLICATIONS

This Utility Patent Application is based on the U.S. Provisional Application for Patent Serial #60/135,488 filed on May 24, 1999.

FIELD OF THE INVENTION

The present invention relates to an apparatus and method for patterned cleaning used in fabrication of a variety of miniature structures such as semiconductor chips, optical, chemical, biological, environmental, physical, and electromagnetic detectors/sensors, mechanical, electromechanical elements, actuators, as well as a wide variety of different electronic components. Particularly, the present invention relates to an apparatus and technique for patterned cleaning of substrate surface applicable in Direct Write processes.

Additionally, the present invention relates to an apparatus and technique for patterned substrate surface cleaning by irradiation of the substrate surface using an energy beam, such as laser beam, ion beam, or electronic beam.

Still further, the present invention relates to a

technique of patterning the surface cleaning, thus allowing cleaning only of the areas of the substrate surface where cleaning is required or is determined to be effective. This insures the efficient utilization of the available energy of the laser (as well as ion or electron) radiation to thus allow cleaning of substrates that may contain sensitive components or areas that are intolerant to the impinging radiation.

The present invention particularly relates to techniques employing Laser Direct Write and Laser Forward Transfer processes to manufacture complex circuits or miniature structures on a wide variety of substrates.

Further, the present invention relates to an apparatus and technique in which cleaning and deposition processes are carried out with the same fabrication tool, without removing the substrate therefrom. In this manner, miniature structures are fabricated by controllably changing the relative position between an energy beam and the substrate to remove a pattern of surface contamination from the substrate or from material previously deposited on the substrate. Subsequently and without removing the substrate from the fabrication tool, the relative position between the energy beam and the substrate is controllably adjusted to transfer a pattern of depositable material to the areas freshly exposed on the substrate surface thus creating desired miniature structures thereon. If needed,

and still without removing the substrate from the
fabrication tool, the relative position between the energy
beam and the substrate may be further adjusted to remove a
second pattern of the surface contamination from the
substrate and/or from the material transferred to the
substrate.

5

10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65
66
67
68
69
70
71
72
73
74
75
76
77
78
79
80
81
82
83
84
85
86
87
88
89
90
91
92
93
94
95
96
97
98
99
100
101
102
103
104
105
106
107
108
109
110
111
112
113
114
115
116
117
118
119
120
121
122
123
124
125
126
127
128
129
130
131
132
133
134
135
136
137
138
139
140
141
142
143
144
145
146
147
148
149
150
151
152
153
154
155
156
157
158
159
160
161
162
163
164
165
166
167
168
169
170
171
172
173
174
175
176
177
178
179
180
181
182
183
184
185
186
187
188
189
190
191
192
193
194
195
196
197
198
199
200
201
202
203
204
205
206
207
208
209
210
211
212
213
214
215
216
217
218
219
220
221
222
223
224
225
226
227
228
229
230
231
232
233
234
235
236
237
238
239
240
241
242
243
244
245
246
247
248
249
250
251
252
253
254
255
256
257
258
259
260
261
262
263
264
265
266
267
268
269
270
271
272
273
274
275
276
277
278
279
280
281
282
283
284
285
286
287
288
289
290
291
292
293
294
295
296
297
298
299
300
301
302
303
304
305
306
307
308
309
310
311
312
313
314
315
316
317
318
319
320
321
322
323
324
325
326
327
328
329
330
331
332
333
334
335
336
337
338
339
340
341
342
343
344
345
346
347
348
349
350
351
352
353
354
355
356
357
358
359
360
361
362
363
364
365
366
367
368
369
370
371
372
373
374
375
376
377
378
379
380
381
382
383
384
385
386
387
388
389
390
391
392
393
394
395
396
397
398
399
400
401
402
403
404
405
406
407
408
409
410
411
412
413
414
415
416
417
418
419
420
421
422
423
424
425
426
427
428
429
430
431
432
433
434
435
436
437
438
439
440
441
442
443
444
445
446
447
448
449
450
451
452
453
454
455
456
457
458
459
460
461
462
463
464
465
466
467
468
469
470
471
472
473
474
475
476
477
478
479
480
481
482
483
484
485
486
487
488
489
490
491
492
493
494
495
496
497
498
499
500
501
502
503
504
505
506
507
508
509
510
511
512
513
514
515
516
517
518
519
520
521
522
523
524
525
526
527
528
529
530
531
532
533
534
535
536
537
538
539
540
541
542
543
544
545
546
547
548
549
550
551
552
553
554
555
556
557
558
559
560
561
562
563
564
565
566
567
568
569
570
571
572
573
574
575
576
577
578
579
580
581
582
583
584
585
586
587
588
589
590
591
592
593
594
595
596
597
598
599
600
601
602
603
604
605
606
607
608
609
610
611
612
613
614
615
616
617
618
619
620
621
622
623
624
625
626
627
628
629
630
631
632
633
634
635
636
637
638
639
640
641
642
643
644
645
646
647
648
649
650
651
652
653
654
655
656
657
658
659
660
661
662
663
664
665
666
667
668
669
670
671
672
673
674
675
676
677
678
679
680
681
682
683
684
685
686
687
688
689
690
691
692
693
694
695
696
697
698
699
700
701
702
703
704
705
706
707
708
709
710
711
712
713
714
715
716
717
718
719
720
721
722
723
724
725
726
727
728
729
730
731
732
733
734
735
736
737
738
739
740
741
742
743
744
745
746
747
748
749
750
751
752
753
754
755
756
757
758
759
760
761
762
763
764
765
766
767
768
769
770
771
772
773
774
775
776
777
778
779
780
781
782
783
784
785
786
787
788
789
790
791
792
793
794
795
796
797
798
799
800
801
802
803
804
805
806
807
808
809
810
811
812
813
814
815
816
817
818
819
820
821
822
823
824
825
826
827
828
829
830
831
832
833
834
835
836
837
838
839
840
841
842
843
844
845
846
847
848
849
850
851
852
853
854
855
856
857
858
859
860
861
862
863
864
865
866
867
868
869
870
871
872
873
874
875
876
877
878
879
880
881
882
883
884
885
886
887
888
889
890
891
892
893
894
895
896
897
898
899
900
901
902
903
904
905
906
907
908
909
910
911
912
913
914
915
916
917
918
919
920
921
922
923
924
925
926
927
928
929
930
931
932
933
934
935
936
937
938
939
940
941
942
943
944
945
946
947
948
949
950
951
952
953
954
955
956
957
958
959
960
961
962
963
964
965
966
967
968
969
970
971
972
973
974
975
976
977
978
979
980
981
982
983
984
985
986
987
988
989
990
991
992
993
994
995
996
997
998
999
1000
1001
1002
1003
1004
1005
1006
1007
1008
1009
1010
1011
1012
1013
1014
1015
1016
1017
1018
1019
1020
1021
1022
1023
1024
1025
1026
1027
1028
1029
1030
1031
1032
1033
1034
1035
1036
1037
1038
1039
1040
1041
1042
1043
1044
1045
1046
1047
1048
1049
1050
1051
1052
1053
1054
1055
1056
1057
1058
1059
1060
1061
1062
1063
1064
1065
1066
1067
1068
1069
1070
1071
1072
1073
1074
1075
1076
1077
1078
1079
1080
1081
1082
1083
1084
1085
1086
1087
1088
1089
1090
1091
1092
1093
1094
1095
1096
1097
1098
1099
1100
1101
1102
1103
1104
1105
1106
1107
1108
1109
1110
1111
1112
1113
1114
1115
1116
1117
1118
1119
1120
1121
1122
1123
1124
1125
1126
1127
1128
1129
1130
1131
1132
1133
1134
1135
1136
1137
1138
1139
1140
1141
1142
1143
1144
1145
1146
1147
1148
1149
1150
1151
1152
1153
1154
1155
1156
1157
1158
1159
1160
1161
1162
1163
1164
1165
1166
1167
1168
1169
1170
1171
1172
1173
1174
1175
1176
1177
1178
1179
1180
1181
1182
1183
1184
1185
1186
1187
1188
1189
1190
1191
1192
1193
1194
1195
1196
1197
1198
1199
1200
1201
1202
1203
1204
1205
1206
1207
1208
1209
1210
1211
1212
1213
1214
1215
1216
1217
1218
1219
1220
1221
1222
1223
1224
1225
1226
1227
1228
1229
1230
1231
1232
1233
1234
1235
1236
1237
1238
1239
1240
1241
1242
1243
1244
1245
1246
1247
1248
1249
1250
1251
1252
1253
1254
1255
1256
1257
1258
1259
1260
1261
1262
1263
1264
1265
1266
1267
1268
1269
1270
1271
1272
1273
1274
1275
1276
1277
1278
1279
1280
1281
1282
1283
1284
1285
1286
1287
1288
1289
1290
1291
1292
1293
1294
1295
1296
1297
1298
1299
1300
1301
1302
1303
1304
1305
1306
1307
1308
1309
1310
1311
1312
1313
1314
1315
1316
1317
1318
1319
1320
1321
1322
1323
1324
1325
1326
1327
1328
1329
1330
1331
1332
1333
1334
1335
1336
1337
1338
1339
1340
1341
1342
1343
1344
1345
1346
1347
1348
1349
1350
1351
1352
1353
1354
1355
1356
1357
1358
1359
1360
1361
1362
1363
1364
1365
1366
1367
1368
1369
1370
1371
1372
1373
1374
1375
1376
1377
1378
1379
1380
1381
1382
1383
1384
1385
1386
1387
1388
1389
1390
1391
1392
1393
1394
1395
1396
1397
1398
1399
1400
1401
1402
1403
1404
1405
1406
1407
1408
1409
1410
1411
1412
1413
1414
1415
1416
1417
1418
1419
1420
1421
1422
1423
1424
1425
1426
1427
1428
1429
1430
1431
1432
1433
1434
1435
1436
1437
1438
1439
1440
1441
1442
1443
1444
1445
1446
1447
1448
1449
1450
1451
1452
1453
1454
1455
1456
1457
1458
1459
1460
1461
1462
1463
1464
1465
1466
1467
1468
1469
1470
1471
1472
1473
1474
1475
1476
1477
1478
1479
1480
1481
1482
1483
1484
1485
1486
1487
1488
1489
1490
1491
1492
1493
1494
1495
1496
1497
1498
1499
1500
1501
1502
1503
1504
1505
1506
1507
1508
1509
1510
1511
1512
1513
1514
1515
1516
1517
1518
1519
1520
1521
1522
1523
1524
1525
1526
1527
1528
1529
1530
1531
1532
1533
1534
1535
1536
1537
1538
1539
1540
1541
1542
1543
1544
1545
1546
1547
1548
1549
1550
1551
1552
1553
1554
1555
1556
1557
1558
1559
1560
1561
1562
1563
1564
1565
1566
1567
1568
1569
1570
1571
1572
1573
1574
1575
1576
1577
1578
1579
1580
1581
1582
1583
1584
1585
1586
1587
1588
1589
1590
1591
1592
1593
1594
1595
1596
1597
1598
1599
1600
1601
1602
1603
1604
1605
1606
1607
1608
1609
1610
1611
1612
1613
1614
1615
1616
1617
1618
1619
1620
1621
1622
1623
1624
1625
1626
1627
1628
1629
1630
1631
1632
1633
1634
1635
1636
1637
1638
1639
1640
1641
1642
1643
1644
1645
1646
1647
1648
1649
1650
1651
1652
1653
1654
1655
1656
1657
1658
1659
1660
1661
1662
1663
1664
1665
1666
1667
1668
1669
1670
1671
1672
1673
1674
1675
1676
1677
1678
1679
1680
1681
1682
1683
1684
1685
1686
1687
1688
1689
1690
1691
1692
1693
1694
1695
1696
1697
1698
1699
1700
1701
1702
1703
1704
1705
1706
1707
1708
1709
1710
1711
1712
1713
1714
1715
1716
1717
1718
1719
1720
1721
1722
1723
1724
1725
1726
1727
1728
1729
1730
1731
1732
1733
1734
1735
1736
1737
1738
1739
1740
1741
1742
1743
1744
1745
1746
1747
1748
1749
1750
1751
1752
1753
1754
1755
1756
1757
1758
1759
1760
1761
1762
1763
1764
1765
1766
1767
1768
1769
1770
1771
1772
1773
1774
1775
1776
1777
1778
1779
1780
1781
1782
1783
1784
1785
1786
1787
1788
1789
1790
1791
1792
1793
1794
1795
1796
1797
1798
1799
1800
1801
1802
1803
1804
1805
1806
1807
1808
1809
1810
1811
1812
1813
1814
1815
1816
1817
1818
1819
1820
1821
1822
1823
1824
1825
1826
1827
1828
1829
1830
1831
1832
1833
1834
1835
1836
1837
1838
1839
1840
1841
1842
1843
1844
1845
1846
1847
1848
1849
1850
1851
1852
1853
1854
1855
1856
1857
1858
1859
1860
1861
1862
1863
1864
1865
1866
1867
1868
1869
1870
1871
1872
1873
1874
1875
1876
1877
1878
1879
1880
1881
1882
1883
1884
1885
1886
1887
1888
1889
1890
1891
1892
1893
1894
1895
1896
1897
1898
1899
1900
1901
1902
1903
1904
1905
1906
1907
1908
1909
1910
1911
1912
1913
1914
1915
1916
1917
1918
1919
1920
1921
1922
1923
1924
1925
1926
1927
1928
1929
1930
1931
1932
1933
1934
1935
1936
1937
1938
1939
1940
1941
1942
1943
1944
1945
1946
1947
1948
1949
1950
1951
1952
1953
1954
1955
1956
1957
1958
1959
1960
1961
1962
1963
1964
1965
1966
1967
1968
1969
1970
1971
1972
1973
1974
1975
1976
1977
1978
1979
1980
1981
1982
1983
1984
1985
1986
1987
1988
1989
1990
1991
1992
1993
1994
1995
1996
1997
1998
1999
2000
2001
2002
2003
2004
2005
2006
2007
2008
2009
2010
2011
2012
2013
2014
2015
2016
2017
2018
2019
2020
2021
2022
2023
2024
2025
2026
2027
2028
2029
2030
2031
2032
2033
2034
2035
2036
2037
2038
2039
2040
2041
2042
2043
2044
2045
2046
2047
2048
2049
2050
2051
2052
2053
2054
2055
2056
2057
2058
2059
2060
2061
2062
2063
2064
2065
2066
2067
2068
2069
2070
2071
2072
2073
2074
2075
2076
2077
2078
2079
2080
2081
2082
2083
2084
2085
2086
2087
2088
2089
2090
2091
2092
2093
2094
2095
2096
2097
2098
2099
2100
2101
2102
2103
2104
2105
2106
2107
2108
2109
2110
2111
2112
2113
2114
2115
2116
2117
2118
2119
2120
2121
2122
2123
2124
2125
2126
2127
2128
2129
2130
2131
2132
2133
2134
2135
2136
2137
2138
2139
2140
2141
2142
2143
2144
2145
2146
2147
2148
2149
2150
2151
2152
2153
2154
2155
2156
2157
2158
2159
2160
2161
2162
2163
2164
2165
2166
2167
2168
2169
2170
2171
2172
2173
2174
2175
2176
2177
2178
2179
2180
2181
2182
2183
2184
2185
2186
2187
2188
2189
2190
2191
2192
2193
2194
2195
2196
2197
2198
2199
2200
2201
2202
2203
2204
2205
2206
2207
2208
2209
2210
2

BACKGROUND OF THE INVENTION

Miniaturized electrical components are widely used in a variety of consumer and industrial items, such as TV sets, radios, cars, kitchen appliances, computers, etc. Advantages both in performance and price of miniature structures have made them common in the everyday life of consumers. Due to the popularity and need for miniature structures, such as computer chips, optical, chemical, biological, environmental, physical and electromagnetic detectors/sensors, and a variety of different types of passive electronic components, different manufacturing processes have been developed for fabrication of those structures.

These methodologies may include Direct Write processes, such as Laser Forward Transfer, or Laser Induced Forward Transfer techniques which require a depositable material to be transferred toward a substrate and deposited thereon to manufacture a single structure or a plurality of structures on the same substrate.

In the fabrication of miniature structures, subtractive processes using irradiation of the substrate surface to ablate, evaporate, or otherwise remove material from the workpiece may be employed simultaneously. Laser surface cleaning is a well-known technique for removing surface contaminations such as particulate matter, thin layers of oil, or other organic/inorganic contaminants.

Laser surface cleaning is carried out prior to the deposition of a depositable material on the surface of the substrate to promote adherence of the depositable material to the substrate surface and to enhance electrical contact.

5 Although being well developed and known to those skilled in the art, conventional irradiation surface cleaning has several drawbacks. Particularly, during the irradiation surface cleaning, substantially the entire surface of a substrate may be affected by irradiation including areas containing fragile or sensitive components as well as areas that are intolerant of laser, ion, or electron radiation. Such a wide area impingement may cause damage to the components located on the substrate surface.

10 Additionally, radiation of the entire substrate surface consumes more laser energy than needed for the cleaning process, thus reducing the efficiency of the available laser energy.

15 Another drawback of conventional surface cleaning is encountered when a plurality of different materials exist on the substrate surface requiring different fluences of the laser beam to be cleaned or removed. Usually, these materials are spread over the substrate surface at different locations. Conventional cleaning (in which the entire substrate surface may be irradiated by the laser beam of the same intensity) cannot selectively clean
20
25 separate areas containing different materials without

complicating the process with additional steps such as the use of masks, photoresists, and other blocking mechanisms.

Still another drawback of conventional cleaning processes is related to the necessity of transferring the cleaned substrate from the "cleaning area" to a "deposition area". During substrate transfer from one area to another, physical damage to the workpiece may occur. Additionally, the workpiece may be contaminated and the freshly exposed areas on the surface may be reoxidized, thus substantially reducing yield of high quality devices.

Accordingly, despite certain utility of the conventional manufacturing equipment and techniques for fabrication of miniature structures, particularly surface cleaning, a long-felt need exists for equipment and techniques in which surface cleaning and deposition may be carried out with the same fabrication tool which provides for selective surface cleaning of those areas where it is required or is effective. A need also has existed for insuring efficient utilization of available laser, ion, or electron energy, where the unwanted irradiation of surfaces containing fragile components or areas intolerant of radiation may be avoided as well as where the cleaning of the surfaces containing a plurality of different materials may be carried out in a simple and effective manner.

SUMMARY OF THE INVENTION

It is therefore an object of the present invention to provide a fabrication tool and method for patterned cleaning of a substrate surface in which only required areas of the substrate surface are cleaned, thus avoiding undesirable areas of the substrate surface to be effected by radiation.

It is another object of the present invention to provide an apparatus and technique for patterned cleaning of a substrate surface using available radiation energy in a highly efficient manner in order to reduce consumption of the radiation energy needed for a manufacturing process which ultimately reduces the cost of the manufacturing process and resulting product.

It is still a further object of the present invention to provide a method and apparatus for patterned cleaning of the substrate surface in which a plurality of different materials are to be cleaned and removed by scanning the energetic or energy beam over the to-be-cleaned areas of the substrate surface in a patterned fashion with simultaneous adjustment of the energy beam intensity as a function of each material located on the substrate surface.

It is still a further object of the present invention to provide an apparatus and technique for fabrication of miniature structures in which both the cleaning process and deposition process are carried out with the same

5 fabrication tool without removing the substrate from the site. This avoids possible physical damage to the workpiece or contamination as well as unwanted reoxidation of freshly exposed areas of the substrate surface thereby increasing the yield of the high quality miniature structures and reducing the cost of and simplifying the manufacturing process.

10 It is a further object of the present invention to provide an apparatus for fabrication of miniature structures in which a control unit operates the apparatus in either a "material removal" or "material transfer" mode of operation in order that in the same apparatus, either a cleaning of the surface, or deposition of a depositable material on the cleaned surface of the substrate may be
15 controlled in a predetermined patterned sequence.

20 It is an object of the present invention to provide an apparatus for manufacturing of miniature structures in which during a "material removal" mode of operation, a control unit controls a direct impingement of the energy beam onto the surface of the substrate in order that the energy beam scans the surface of the substrate in a patterned fashion and selectively removes unwanted material from the substrate surface. Using the same apparatus during the "material transfer" mode of operation, the
25 control unit displaces a source of depositable material in an intercepting path with the energy beam, so that the

energy beam impinges the source of depositable material and causes transference of the depositable material towards the surface of the substrate with such being deposited in a patterned fashion onto the areas freshly exposed during the preceding cleaning step.

Another object of the present invention is to provide an apparatus for cleaning of the substrate surface and for manufacturing miniature structures on a substrate surface in which a carrier gas is supplied to the fabrication tool which purges produced residues. Additionally, an inert cover gas may be supplied to flow through the fabrication tool to prevent reoxidation of freshly exposed areas of the substrate surface thus promoting adhesion of the depositable materials, minimizing material contamination, improving bonding and decreasing electrical contact resistance.

Still further the present invention provides a cleaning process for a substrate surface particularly adaptable for cleaning of surfaces having a plurality of different materials mounted thereon. Simultaneously in this process, the energy beam is "scanned" over the areas where different materials are positioned and the intensity of the energetic beam is fine-tuned as a function of the materials position.

Further the present invention provides a fabrication tool and method for manufacturing miniature structures

using a controlled atmosphere and minimized surface exposure time (between patterned cleaning and subsequent deposition) which can greatly improve adhesion of deposited films.

5 In accordance with the present invention, a fabrication tool for patterned cleaning of a substrate surface includes a substrate, a source of an energy beam directed towards the substrate, a material carrier element having a deposition layer thereon, and a control unit
10 operating the fabrication tool in either a "material removal" mode of operation, or a "material transfer" mode of operation in a specified sequence.

15 In the "material removal" mode of operation, the control unit changes the relative disposition between the energetic beam and the substrate in accordance with a predetermined pattern to clean the substrate surface in a patterned fashion. After the cleaning step has been performed, the control unit transfers the fabrication tool
20 into the "material transfer" mode of operation by displacing the material carrier element in a position intersecting the energy beam and further changes the relative distance between the energy beam and the substrate in accordance with a predetermined pattern. This pattern
25 may be the same as the pattern of the "material removal" mode of operation, thus transferring the depositable material from the material carrier element towards the

substrate and depositing the depositable material on the areas freshly exposed during the cleaning process.

The control unit may further transfer the fabrication tool to another "material removal" mode of operation by displacing the material carrier element away from an interception path with energy beam for further surface cleaning. In this instance, the surface to be cleaned contains deposited miniature structures. In a second surface cleaning, the substrate surface is cleaned in a patterned fashion in accordance with a second pattern (which may be distinct from the first pattern) for further deposition of structures on the freshly exposed areas.

The energy beam may be a laser beam, ion beam, or electron beam. Particularly, the laser beam may be a pulsed ultraviolet beam which due to the short absorption depth of UV radiation, prevents deep penetration and widespread thermal damage of the substrate surface. Ultraviolet radiation may also create ions more effectively than that of radiation at longer wavelengths. The created ions may contribute in static charge neutralization which is believed to be an important mechanism in removing particles from surfaces.

The deposition layer on the material carrier element contains a depositable material which may include powders, metals, composites, alloys, ceramics, a vaporizable substance, molecular precursors, and/or solvents. The

materials carrier element is made transparent to the UV radiation to allow direct access for the energy beam to the deposition layer.

5 A typical substrate may contain many different materials each with different radiation fluence requirement for cleaning. By adjusting the energy beam intensity under computer control through a variable attenuator, acousto-optics modulator, or other means, while moving the
10 workpiece and/or scanning the beam, allows the tailoring or fine-tuning of the energy beam fluence as a function of each material position.

15 Preferably, the fabrication tool includes a mechanism for supplying either a carrier gas or an inert cover gas flowing through the fabrication tool during the cleaning process for removing residues formed during the surface cleaning and for preventing re-oxidation of areas on the substrate surface freshly exposed during the cleaning.

20 Another aspect of the present invention is directed to a method of patterned cleaning of a substrate surface in a fabrication tool operated in either a "material removal" mode of operation and/or a "material transfer" mode of operation. The "material removal" mode of operation includes the steps of performing a first cleaning of the substrate surface by changing a relative disposition
25 between the energy beam and the substrate in accordance with a first pattern, and performing a second cleaning of

the substrate surface by changing a relative distance between the energy beam and the substrate in accordance with a second pattern.

Between the first and second cleaning, the control unit of the fabrication tool positions a material carrier element having a deposition layer into an intercepting path with the energy beam, thus translating the fabrication tool in the "material transfer" mode of operation. By changing the relative distance between the energy beam and the substrate in accordance with the first predetermined pattern there is caused a deposition of depositable material contained in the deposition layer onto the substrate surface at locations freshly exposed during the first cleaning of the substrate surface.

Additionally, the present invention is directed to a method for fabrication of miniature structures in a unique fabrication tool which includes a substrate, a controllable energetic beam directed towards the substrate, a material carrier element having a deposition layer supported thereon facing the substrate, and a control unit operating the fabrication tool in either "material removal" mode of operation and "material transfer" mode of operation in a predetermined sequence. In the "material removal" mode of operation, the material carrier element is displaced from interception with energy beam and thus provides an unimpeded path for the energy beam to the surface of the

substrate. Simultaneously, the relative disposition or distance between the energy beam and the substrate is varied in accordance with a first predetermined pattern.

5 In the "material transfer" mode of operation following the patterned cleaning, the material carrier element is displaced into interception with the energy beam and the relative distance between the energy beam and the substrate is changed in accordance with the first predetermined pattern, thereby transferring and depositing a depositable material contained in the deposition layer on the surface of the substrate cleaned during the first cleaning process.

10 After the material deposition has been carried out, the manufacturing process continues to the next step of translating the fabrication tool again into the "material removal" mode of operation and performing the second cleaning by changing the relative disposition or distance between the energy beam and the substrate in accordance with a second predetermined pattern. In the second cleaning, the surface of the substrate includes the structures deposited thereon during the material transfer mode of operation.

15 During the first or second cleaning process the substrate surface has a plurality of different materials thereon requiring different intensities of the energy beam for their disintegration. The control unit provides not only for the energy beam to scan over the surface of the

20

25

substrate and/or for the workpiece to move with regard to the energy beam, but also changes the intensity of the energy beam as a function of position of each particular material on the substrate surface.

5 The technique of the present invention also includes the possibility of controlling atmosphere within the fabrication tool to remove the residues from the surface formed during the cleaning process and to prevent freshly exposed areas from undesired reoxidation by controlling the
10 atmosphere within the fabrication tool and by supplying either carrier gas or inert cover gas flowing through the fabrication tool.

15 These and other novel features and advantages of this invention will be fully understood from the following detailed description of the accompanying Drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a schematic representation of the apparatus for fabrication of miniature structures of the present invention;

5 FIG. 2A is a schematic representation of the apparatus of the present invention operating in "material removal" mode of operation to perform a first surface cleaning;

10 FIG. 2B is a schematic representation of the apparatus of the present invention operating in a "material transfer" mode of operation in which the material deposition is carried out; and

FIG. 2C is a schematic representation of the apparatus of the present invention operating in a "material removal" mode of operation to perform a second surface cleaning;

15 FIG. 3 is an overall block diagram of the apparatus of the present invention;

FIG. 4 is a block diagram of a controller subsystem of the apparatus of the present invention coordinating the substrate motion and laser activation-deactivation;

20 FIG. 5 is a block diagram of a controller subsystem for laser motion and laser actuation-deactuation control of the apparatus of the present invention;

FIG. 6 is a block diagram of the beam control subsystem of the apparatus of the present invention; and

FIG. 7 is a flow chart diagram of the computer program driving the control unit of the apparatus of the present invention.

FIG. 7 is a flow chart diagram of the computer program driving the control unit of the apparatus of the present invention.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENT

The present invention provides a unique implementation and enhances the ability of laser direct write (LDW) and laser forward transfer (LFT) processes to create complex circuits or structures in a conformal manner on virtually any substrate. Surface cleaning promotes adhesion of deposited materials, minimizes material contamination, improves bonding, and decreases electrical contact resistance.

Patterning the surface cleaning through a direct write process, according to the present invention, permits cleaning only those selective areas where it is required or will be effective. This helps to insure efficient utilization of available laser energy and allows cleaning of substrates that might contain fragile or sensitive components and/or areas that are intolerant of laser radiation.

Referring to FIGS. 1-2C, the apparatus 10 of the present invention includes a substrate 11, a source of energy 12 capable of generating an energy beam 13, a material carrier element 14 which is displaceably located in a gap 15 formed between the source of energy 12 and the substrate 11, a deposition layer 16 supported on the surface 17 of the material carrier element 14, and a control unit 18. The control unit 18 is operatively coupled to the source of energy 12 through a transmission

link 19 and to the material carrier element 14 through the communication link 20. Alternatively, the control unit 18 may be operatively coupled to the substrate 11 through the communication link 21.

5 The control unit 18 actuates the source of energy 12 through the communication link 19 to generate the energy beam 13, regulates the parameters of the energy beam 13 such as fluence, etc., and changes relative position between the energy beam and the substrate in a patterned manner. Accordingly, the control unit 18 "scans" the
10 energy beam 13 over the surface of the substrate 11 either by moving the source of energy 12 in X-Y directions or by changing angular relative disposition of the energy beam 13 with regard to the substrate 11 in a predetermined pattern.

15 In order to change relative disposition between the energy beam 13 and the substrate 11 in a patterned manner, the control unit 18 alternatively can control the workpiece (substrate) 11 through the communication link 21 by either maintaining the energy beam immovable or displacing the
20 energy beam in a coordinated manner with the substrate.

 In order to provide the control unit 18 with a means of manipulating the energy beam 13, the communication link 19 includes an electromechanical mechanism 22 known to those skilled in the art, which is a unit translating the
25 electrical signal from the control unit into mechanical or optical displacement of the source of energy 12. In the

same manner, the communication link 21 has an electromechanical mechanism 23 which translates the electrical signal from the control unit 18 into the mechanical displacement of the substrate 11 in a patterned manner.

Through the communication link 20, the control unit 18 manipulates the material carrier element 14 within the gap 15 along the X-Y directions so that the material carrier element 14 may be displaced either away from any interception with energy beam 13 or to a position intercepting with the energy beam 13. Similar to the mechanisms 22 and 23, a mechanical displacement unit 24 is included within the communication link 20 to translate the signal generated by the control unit 18 into the mechanical displacement of the material carrier element 14.

The control unit 18, as will be discussed in detail in further paragraphs, operates the apparatus 10 of the present invention in two modes of operation: "material removal" mode of operation and "material transfer" mode of operation. In the "material removal" mode of operation, the material carrier element 14 is displaced away from interception with the energy beam 13, while in the "material transfer" mode of operation, the material carrier element 14 intercepts the energy beam 13 path. Thus, the apparatus 10 of the present invention performs both as a Direct Write and a micromachining (DW/MM) machine and

possesses the ability to accomplish pattern tasks such as laser surface cleaning as well as direct deposit of metal, ceramics, polymers, etc. in situ, in an air atmosphere and at room temperature.

5 In the "material removal" mode of operation, a patterned cleaning process of the present invention is carried out, while in the "material transfer" mode of operation, miniature structures are formed by depositing a depositable material from the deposition layer 16 onto the
10 surface of the substrate.

The control unit 18 may be utilized to change the mode of operation of the apparatus 10 in any required sequence. For example, as best shown in Figures 2A-2C, the control unit 18, first sets the apparatus 10 in a "material
15 removal" mode of operation by displacing the material carrier element 14 from interception with energetic beam 13 and performs a first patterned cleaning by changing the relative disposition between the energetic beam 13 and the substrate 11 in accordance with a first predetermined
20 pattern (as particularly shown in FIG. 2A).

After the first cleaning has been carried out, the control unit 18 changes the mode of operation of the apparatus 10 into the "material transfer" mode of operation by moving the material carrier element 14 into a position
25 intercepting the energy beam 13. A deposition step of the method of the present invention is performed by changing

relative distance or disposition between the energy beam 13 and the substrate 11 in accordance with the first predetermined pattern, thereby depositing a depositable material contained in the deposition layer 16 of the material carrier element 14 onto the substrate surface at locations freshly exposed during the first cleaning, as best shown in FIG. 2B.

After the "material transfer" mode of operation has been accomplished, the control unit 18 changes the mode of operation of the apparatus 10 back to the "material removal" mode of operation by displacing the material carrier element 14 from interception with the energetic beam 13 which allows direct access of the energy beam 13 to the surface of the substrate 11. The substrate 11 now has deposited films formed thereon, and by changing relative disposition between the energy beam 13 and the substrate 11 in accordance with a second predetermined pattern, cleaning in a patterned fashion the surface of the substrate 11 is accomplished, as shown in FIG. 2C. The second pattern of the second cleaning usually differs from the first pattern of the first cleaning.

Although not shown in Figures 2A-2C, the manufacturing process may be continued so that after the second cleaning, the control unit 18 will change the mode of operation of the apparatus 10 back into the "material transfer" mode of operation for depositing structures on the areas freshly

exposed during the second cleaning. The manufacturing process of the present invention, thus may continue in this manner and may include a plurality of intermittent "material removal" and "material transfer" modes of operations performed in a required sequence for fabrication of multi-layered or stacked miniature structures known to those skilled in the art.

One of the major advantages of the apparatus and technique of the present invention is that the substrate 11 does not have to be moved from its position when the modes of operation of the apparatus 10 are changed so that any physical damages associated with transportation of the substrate as well as contamination and reoxidation of the freshly exposed areas of the surface of the substrate is avoided.

As shown in FIG. 2A, illustrating the first cleaning performed in a "material removal" mode of operation, the material carrier element 14 is displaced by the control unit 18 from interception with energy beam 13 whereby the energy beam 13 generated by the source of energy 12 impinges directly upon a surface 25 of the substrate 11. Although shown completely removed from the gap 15, the material carrier element 14 may alternatively remain within the gap 15 during the "material removal" mode of operation. In this instance, care must be taken to avoid interception of the deposition layer 16 with the energy beam 13 in order

to allow direct access or a free path of the beam 13 to the substrate 11.

The untreated surface 25 of the substrate 11 may include different contaminations such as particulate matter, thin layers of oils, oxide layers, or other organic contaminants. Thus prior to the cleaning process, the outermost layer of the material on the surface of the substrate 11 is cleaned and removed before the deposition of intended materials in order to provide effective adhesion of the depositable materials to the surface of the substrate 11.

Therefore, in the first cleaning process, shown in FIG. 2A, the energy beam 13 impinges on the surface 25 of the substrate 11 in a predetermined patterned fashion or manner and removes contaminants or other unwanted materials from the surface 25 at locations 26 thereof under "supervision" of the control unit 18 which changes relative disposition between the energy beam 13 and the substrate 11.

The control unit 18 includes processing means which store in memory predetermined patterns for cleaning the surface 25, i.e., "prescribed paths" for the energy beam 13 and which changes the relative disposition between the energy beam 13 and the substrate 11 according to the stored data.

As discussed in previous paragraphs, the control unit

18 may change the relative disposition between the energetic beam 13 and the substrate 11 in three ways: either scanning the energy beam 13 over the surface of the substrate 11 through the communication link 19; moving the substrate 11 through the communication link 21; or both in coordinated fashion. The control signal is transmitted from the control unit 18 to the source of energy 12 or to the substrate 11 and translated by the mechanism 22 and the mechanism 23, respectively, into mechanical displacement of the energy beam 13 or the substrate 11 and such signal generated in accordance with the data recorded in the memory of the control unit 18.

During the cleaning process, carrier gas 27 is supplied into the apparatus 10 through the inlet 28 (best shown in Figure 1) to purge the laser produced residue formed on the surface 25 of the substrate 11. At the end of the cleaning process when the freshly exposed areas at locations 26 are vulnerable to the atmosphere within the fabrication tool of the apparatus 10, an inert cover gas 29 is supplied into the apparatus 10 either through the inlet 28 or through a separate inlet 30 which flows through the apparatus 10 to prevent reoxidation of freshly exposed materials at locations 26 that might otherwise rapidly diminish the possibility of bonding of the depositable material to the surface 25.

When the first cleaning process has been completed,

the control unit 18 changes the mode of operation of the apparatus 10 to the "material transfer" mode of operation, best shown in FIG. 2B by moving the material carrier element 14 into the gap 15 formed between the substrate 11 and the source of energy 12.

In this mode of operation, the control unit changes a relative disposition between the energy beam 13 and the substrate 11 (either by scanning the energy beam 13 with respect to the immovable substrate 11, or by moving the substrate 11 with respect to the immovable energy beam 13, or moving both the beam 13 and the substrate 11).

The energy beam, thus, impinges upon the material carrier element 14 which is transparent to the radiation and modifies the deposition layer 16 so that the depositable material contained in the deposition layer 16 transfers from spots 31 onto the surface 25 of the substrate 11 and is deposited thereon, particularly at locations 26 freshly exposed on the surface 25 of the substrate 11 during the first cleaning process.

In this manner, miniature structures 32 (deposition films) forming electrical components are created at the predetermined locations on the surface of the substrate. Since the deposition takes place at locations freshly opened during the cleaning process, the deposition structures 32 have improved adhesion of the deposited materials to the surface 25. This improves bonding thereto

and minimizes material contamination at the border between the deposited structures 32 and the surface 25 at the locations 26.

5 The transferred pattern of depositable material and the first pattern of removed surface contamination (during the first cleaning) may be substantially the same. The deposition layer 16 includes a depositable material, such as powders, metals, composites, alloys, ceramics, vaporizable substances, molecular precursors and/or
10 solvents.

In many embodiments, the deposition layer 16 includes a vaporizable substance which rapidly decomposes when exposed to the energy beam 13 to propel the other constituents of the deposition material to the substrate
15 11. Powders can be comprised of a distribution of powder sizes to enable a closely packed matrix. The molecular precursors can react to reduce an externally generated densification energy which can be thermal or optical (coherent or incoherent light); or have an exothermic
20 reaction when activated from the energy beam 13.

Once the deposition of miniature structures 32 have been accomplished, another cleaning process may be needed, as shown in FIG. 2C. To perform the second cleaning, the control unit 18 changes the mode of operation of the
25 apparatus 10 to the "material removal" mode of operation by removing the material carrier element 14 from the

interception with the energy beam thus allowing a direct access of the energy beam 13 to the surface 25 of the substrate 11. In the second surface cleaning, the control unit 18 changes the relative interposition between the energy beam 13 and the substrate 11 (either by scanning the energy beam 13, or by moving the substrate 11, or both) in a patterned fashion according to a second predetermined pattern which may differ from the first pattern in order to clean the surface 25 of the substrate 11 at other locations 33 different from locations 26 exposed during the first cleaning process. In the second surface cleaning, not only the surface 25 of the substrate 11 is subjected to the cleaning process, but the surfaces of the miniature structures 32 also may be cleaned by the energy beam 13 in order to prepare them for further depositions if needed.

The "material removal" mode of operation, as shown in FIGS. 2A and 2C, are set by removing the material carrier element 14 from the gap 15 formed between the source of energy 12 and the substrate 11 in order not to interfere with the energy beam 13. During the "material removal" mode of operation, it is not necessary to completely remove the material carrier element 14 from the gap 15. It is possible to keep the material carrier element 14 within the gap 15 so that the control unit 18 moves the material carrier element 14 during the cleaning process within the gap 15 maintaining, at each instance, the deposition layer

16 away from intercepting with the beam 13 thus allowing direct access of the energy beam 13 to the surface of the substrate 11.

5 A typical substrate 11 may contain many different materials each with different fluence requirements for cleaning. Adjusting the energy beam intensity under the control of the control unit 18 through a beam controller 34, which may include a variable attenuator, or acousto-optic modulator, or other means known to those skilled in the art (best shown in FIGS. 1, and 3-6), while moving the substrate 11 or scanning the beam 13, permits the tailoring or fine-tuning of the energy beam fluence as a function of position of the different materials on the surface 25 of the substrate 11.

15 The source of energy 12 may be any one of laser, ion gun, or electron gun. When the energy beam 13 is a laser beam, it is preferred that an ultraviolet pulsed excimer laser beam is used for the cleaning process of the present invention. This is due to the fact that short absorption depths of ultraviolet radiation, typically a few nanometers or less, prevents deep penetration and widespread thermal damage.

20 Ultraviolet radiation can also create ions more effectively than that of longer wavelengths which contribute to static charge neutralization which is believed to be an important mechanism in removing particles

from the surface 25 of the substrate 11.

Pulsed ultraviolet lasers are preferred sources of energy for laser surface cleaning of the present invention. The short absorption depths in most materials and the small minimum spot (or feature) size (proportional to wavelength) give ultraviolet lasers many advantages for both the laser forward transfer process and the laser machining process (material removal). The ultraviolet laser, such as an excimer laser, may be pulsed preferably at a rate above 10 Hz and may have a pulse width shorter than 10 microseconds. The ability to exploit all of these technologies is inherent in the design of the apparatus 10 of the present invention.

Since both the material removal (cleaning) and the material deposition are carried out in the same fabrication tool, the surface exposure time between patterned cleaning and subsequent deposition is substantially minimized. Additionally, there is provided the capability to control the atmosphere within the fabrication tool 10 which greatly improves adhesion of deposited films 32 to the cleaned surface of the substrate 11. The system may operate at ambient pressure and temperature and may have a controlled atmosphere (oxidizing, reducing, or inert).

The apparatus 10 and the technique of the present invention employing laser Direct Write and Laser Forward Transfer techniques, also referred to as Direct Write

technologies, offer great potential for high resolution and high speed pattern deposition of a wide range of materials on virtually any flat or three-dimensional (3-D) substrate. The speed of the process can be limited only by the criterion of how fast multiple laser spots can be overlapped. This is an environmentally safe, energy efficient and dry process which can change between different materials as quickly as the materials carrier element can be mechanically translated into the optical path of the energy beam 13. The base equipment of the apparatus 10, which is Direct Write equipment and Micromachining equipment, can be easily computer-controlled and is CAD/CAM compatible. The ability to micromachine (in the "material removal" mode of operation), can prove to be crucial when tight tolerances demand in situ component trimming. The same CAD/CAM control used to pattern deposition of the depositable material or position of the energetic beam can be exploited to create optimum "tool paths" for the cleaning laser 12.

Due to the fact that the apparatus 10 and the technique of the present invention is an optically based approach, it lends itself to several in situ optical diagnostics, i.e., ellipsometry, FTIR, optical pyrometry, etc.

The apparatus 10 and the technique of the present invention employs both pattern additive and subtractive

process in a single machine, in which different products can be manufactured: mechanical, electromechanical, sensor, or electrical devices; electrical elements that can be formed include resistors, capacitors, sensors, inductors, antennae, or batteries. Also during the subtractive process, the apparatus of the present invention creates holes, vias, waveguides, registration marks, gratings, scribe lines, etchings, trimming, in addition to surface cleanings which already have been described in previous paragraphs. The system of the present invention may be used with only a single rough alignment and can be accomplished without registration marks since fabrication which requires extremely accurate alignment may be completed without removing the substrate from the apparatus 10.

The advantages of the fabrication technique of the present invention have been attained due to the design of the apparatus 10, and particularly due to a functional performance and operational approach of the control unit 18, best shown in Figures 3-7. The control unit 18 coordinates all aspects of deposition/ablation process; provides interfacing for an operator control and monitoring; monitors all critical subsystems (including optical systems) of the apparatus 10 for quality control and safety;

provides communication with external systems and databases, both internal and external; and

provides for compatibility with CAD/CAM control.

Referring to Figure 3, showing the overall block
5 diagram of the system of the present invention, the control unit 18 includes a main computer 52, motion/laser controller 53, and a beam controller 34. The main computer 52 interchanges data with the motion/laser controller 53 through the bi-directional communication channel 57.

10 The motion/laser controller 53 is external or internal to the main computer 52, provides accurate (approximately 1 micron) dynamic closed loop position control of the substrate, material carrier element position, and scanning laser beam. The motion-laser controller 53 moves the
15 substrate with high speed (up to 1 meter per second) and accuracy (approximately 1 micron) as well as provides for smoothness of travel for patterned deposition or ablation micromachining. Also, the main computer 52 communicates with the beam controller 34 through the bi-directional
20 communication channel 58.

A substrate fixture 60 includes stages 62 and 63, best shown in FIGS. 3 and 4, which being controlled by the motion/laser controller 53, provide for a required displacement of the substrate 11 in accordance to a
25 prescribed path, as will be described in detail in further paragraphs with reference to Figure 4. The substrate

5 fixture 60 provides for holding the substrate reliably, keeps it at a required level, controls its temperature as well as atmosphere. For controlling and monitoring the displacement and position of the substrate 11, the bi-directional communication link 21 operatively couples the stages 62 and 63 of the substrate fixture 60 with the motion/laser controller 53 to convey control signals to the fixture 60 and readings of the position to the motion/laser controller 53.

10 The motion/laser controller 53 further communicates with the material carrier element 14 through the bi-directional communication channel 20 which has included therein the mechanism 24 responsible for mechanical displacement of the material carrier element 14 either into
15 intercepting position with the laser beam 13 (in the "material transfer" mode of operation) or away from interception with the laser beam 13 (in the "material removal" mode of operation). The mechanism 24 also changes a position of the material carrier element with regard to
20 the laser beam 13 according to the prescribed path for attaining the effective utilization of the depositable material of the deposition layer 16, deposition of a specific depositable material contained in the deposition layer 16, and deposition of the depositable material on an
25 aimed area of the substrate 11. Depending on the type of the material carrier element 14, the mechanism 24 has a

distinctive design features adapted for the particular type of the material carrier element 14 as prescribed by the motion/laser controller 53 through the channel 20. The mechanism 24 may include "reel-to-reel" mechanism, spinning-sliding vacuum system, or other motion actuating mechanisms.

The control unit 18, as can be seen in Figure 3, is operatively coupled to the laser system 12 through the communication channel 19 which includes the communication channel 58 for providing coupling between the main computer 52 and the beam controller 34, and the communication channel 64 for providing a bi-directional coupling between the motion/laser controller 53 and the laser 12, as will be described in detail further with reference to Figures 5 and 6.

The laser 12 provides focusable pulsed energy source serving to:

transfer material from the deposition layer 16 to the substrate 11 in the "material transfer" mode of operation;

ablatively remove the material from the surface of the substrate 11 in the "material removal" mode of operation;

remove foreign material from the substrate and/or prepare and activate from the substrate surface before or after deposition in the "material removal" mode of

operation, particularly "cleaning" mode of operation; and
shape and refine deposited or existing structures
to desired dimensions or values in the "material removal"
mode of operation, particularly "laser trimming" mode of
operation.

As discussed in the previous paragraphs, the
ultraviolet pulsed laser is preferred due to superior
ablation characteristics for many materials. Specifically,
all solid state frequency tripled neodymium-vanadate lasers
(radiating at approximately 355 nm), and frequency
quadrupled energy laser (radiating approximately at 266 nm)
are preferred because they offer high repetition rates,
short pulses, sufficient beam quality, high average power,
and superior reliability at low maintenance. The laser
beam 13 generated by the laser 12, is controlled by the
beam controller 34 under the overall control and monitoring
of the main computer 52. As disclosed in previous
paragraphs, the beam control is embedded in the system 10
of the present invention in order to deliver the laser beam
of the desired optimal laser spot size, shape, and fluence
to the material carrier element 14 or to the surface of the
substrate 11. Beam shape and size determines the
resolution and pattern of the deposition or ablation. Once
the shape, size and fluence of the laser beam 13 has been
attained, the laser beam impinges upon the splitter 65
whereat the laser beam 13 splits into a beam 66 directed to

the objective 67 which further focuses the beam 66 and directs the same to either the surface of the material carrier element 14 or to the surface of the substrate 11. The mirror splitter 65 is a highly reflective at laser wavelength but transparent for invisible spectrum for the video system 69. Another portion of the laser beam 13, particularly the beam 68, is directed by the splitter 65 to a video system 69 which includes a video microscope/video camera 70 and a video monitor 71, best shown in Figure 5. The signal from the video microscope/video camera 70 is supplied through the line 72 to a machine vision system 72 for image capture and processing. The video system/machine vision system permits an operator to accurately position substrate for registration and scaling with existing pattern;

to measure and inspect the substrate; and
to facilitate leveling, focusing and displacement of the substrate and the objective 67 in the direction shown by arrows 73 and 74. The optical subsystem of the apparatus 10 of the present invention which includes the video system 69, video microscope/video camera 70, video monitor 71, and the machine vision system 72 is a well-known machine vision technique and is not intended to be described herein in further detail. The data from the machine vision system 72 are transmitted to the main computer 52 for storing, further processing, and for

communication with the motion/laser controller 53 through the communication channel 57 for further control of the relative disposition between the elements of the system 10, as well as actuation-deactuation of the laser 12.

Referring now to Figure 4, showing a block diagram of the substrate motion/laser controller 53 for substrate motion and laser activation-deactivation control, the motion/laser controller 53, either external or internal to the main computer 52, provides accurate (approximately 1 micron) dynamic closed loop position control of the substrate. In this manner, the controller 53 monitors real time position of the substrate and coordinates the same with generating of laser pulses so that the laser pulses can be triggered with very high alignment accuracy.

It is clear that if the laser beam is delivered at constant repetition rate to either the material carrier element, or the substrate, the pulses tend to "pile up" during acceleration and deceleration of the stages 62, 63, or mechanical displacement mechanism 24, or laser beam displacement mechanism (to be discussed further in detail with the reference to Figure 5) and makes deposition and ablation depth control difficult. To obviate these unwanted phenomena, the actuation of the laser is to be coordinated with deposition of the substrate, laser beam, and/or material carrier element in real time fashion. As best shown in Figure 4, the main computer 52, through the

motion-laser controller 53, transmits signals representative of a prescribed path (received from the "Design Concept" block 75 of the Figure 3) which is a CAD/CAM developed design concept for layout of miniature structures cleaning layout) is supplied to the motion control board 77 via a channel 78. The motion control board 77 in accordance with the prescribed path controls an X-motor 79 and a Y-motor 80 to force the stages 62 and 63 carrying the substrate 11 to move the same in required direction a required distance. At the same time, an X-encoder 81 is coupled to the X-stage 62, and the Y-encoder 82 is coupled to the Y-stage 63 for measuring X and Y displacements of the stages 62, 63 and translating them into the format understood by the motor control board 77 and the processing block 83. The data from X-encoder 81 and Y-encoder 82 are supplied through the channels 84 and 85, respectively to the motion control board for being processed and used for generating various control signals outputted through outputs 86. These control signals may be further transmitted to the optical system of the laser for controlling the laser shutters, laser optical zoom, aperture selection, etc.

Simultaneously, the data corresponding to X and Y displacements of the stages 62 and 63 are transmitted from the X-encoder 81 and Y-encoder 82 through the communication links 87 and 88, respectively, to the processing block 83

wherein the X and Y displacements are processed and calculated according to the formula ($\frac{X^2 + Y^2}{m}$), wherein X is a displacement of the stage 62, Y is Y displacement of the stage 63 and m is an integer defining the number of pulses for each displacement vector. The data from the processing block 83 is outputted through the channel 89 to a "distance-to-pulse out" converter 90. The converter 90 thus receives vector displacement increment and in response thereto, generates trigger pulse which is transmitted to the laser 12 through the line 91 for actuating-deactuating the laser 12. Thus, the laser 12 generates laser beam 13 once a required displacement of the substrate 11 has been attained. The "distance-to-pulse out" converter 90 is a converter manufactured by Aerotech, Inc. for operation of the known micromachining stations.

As was described in previous paragraphs, change of the relative disposition between the laser beam, substrate and/or material carrier element, may be implemented in following three fashions:

movement of the substrate with respect to the immovable laser beam; scanning of the laser beam with regard to the substrate and/or material carrier element; and combinatorial motion of the substrate and the laser beam. Thus, when scanning of the laser beam with respect to the substrate and/or material carrier element is chosen for operation, the system 10 of the present invention will

operate in accordance with Figure 5, illustrating the motion/laser controller 53, particularly, a subsystem thereof for laser motion and laser actuation-deactuation control. As shown in Figure 5, data representative of the prescribed path 76 are supplied to the motion control board 92 (which may coincide with the motion control board 77). The motion control board 92, in the manner described with respect to Figure 4, transmits control signal over the line 94 either to the optical system of the laser 12 or to mechanical stages carrying the laser 12 for displacement of the laser beam generated by the laser 12, thus providing scanning of the laser beam over the surface of the material carrier element 14 or the substrate 11. X and Y encoders 95 and 96, or other means sensing displacement of the scanning laser beam receive information from the "optical system/stages" unit 93 of the laser 12 and transmit this information to a processing block 97 which processes the information received from the encoder 95, 96 either in the same manner as the processing block 83 of Figure 4, or in any other fashion known to those skilled in the art, and outputs the data representative of the displacement of the laser beam through the line 98 to the "distance-to-pulse out" converter 90 which in well-known manner converts the data representative of the displacement of the scanning laser beam into the controlling trigger pulses which are supplied to the laser 12 through the line 100 for

actuating/ deactuating the laser 12. The generated laser beam 13 is further controlled by the beam controller 34 and is further directed to the material carrier element 14 or the substrate 11 as described in the previous paragraphs.

5 In this manner, the firing of the laser beam will be coordinated in precise fashion with the scanning of the laser beam with regard to the substrate 11 or the material carrier element 14.

Referring to Figure 6, the beam controller 34 facilitates in delivery of the laser beam of the desired optimal laser spot size, shape, and fluence to the substrate or to the material carrier element. The beam controller 55 includes an acousto-optic modulator 101 coupled to the laser 12 for convenient and efficient way to rapidly (faster than 100 ms) shutter the laser "on" or "off" as well as to control the energy of the individual generated laser pulses dynamically. The acousto-optic modulator 101 external to the laser cavity allows the laser to run at constant repetition rate for maximum stability.

20 Throughput efficiency of the acousto-optic modulator can be controlled by the motion/laser controller 53 in the range between 0% to more than 90%.

A beam shaping optics 102 is coupled to the acousto-optic modulator 101 to control size and shape of the laser beam at the target. The beam shaping optics 102 includes an optical zoom shaped aperture array, and/or diffracted

optic beam shaper.

The control of the power and generation of the laser beam is an important feature since fluences of the generated laser beam are to be maintained at different levels for different purposes. For instance, for deposition, an optimal fluence is kept usually in the range of 0.2 - 2.0 J/Cm² per pulse. For ablation micromachining, generally high fluences are desired for maximum speed and efficiency, typically approximately 1-100 J/CM² per pulse. Lower fluences, approximately 0.2 - 2.0 J/CM² can be used for precise depth control. Using the structure of the system of the present invention, sub-micron depth control has been demonstrated.

The laser beam having the required fluence (provided by the acousto-optical modulator 101) and required size and shape (provided by the beam shaping optics 102) is further outputted to the splitter 65 for further traveling to the target (material carrier elements 14 or the substrate 11) through the objective 67. The objective 67 is provided for final imaging of the UV laser beam and video magnification. The objective 67 is mounted on a focusing stage providing displacement in the direction shown by arrows 73 to permit proper imaging regardless of the substrate height, and regardless of whether the material carrier element is in the beam path.

A detector 103 monitors laser pulse energy and

supplies data representative of the real time laser beam energy to the control unit 18 for closed loop control.

Referring to Figure 7, showing a block diagram of the computer operational principles of the control unit of the apparatus of the present invention, the flow chart initiates with the block 110 corresponding to the pre-start-up procedure which includes alignment of the elements (substrate, material carrier element, laser beam) of the system, registration and positioning. Initially, the material carrier element is maintained in an interception path position with the laser. From the block 110, the logic moves to the decision block 112 "Deposition or subtraction mode?" If a subtraction (cleaning mode of operation) is chosen, the logic is directed to the block 114 "Remove material carrier element from the beam path". In accordance with the command of the block 114, the control unit 18 then outputs a control signal to mechanism 24, best shown in Figure 3, for moving the material carrier element 14 away from the interception position with the laser beam 13.

From the block 114, the logic is directed to the block 116 "Translate substrate (or beam) along prescribed path".

If in the logic block 112, the deposition ("material transfer" mode of operation) is chosen, the operational procedure moves again to the block 116. The logic block 116 receives a desired pattern path which corresponds to

the prescribed path 76 best shown in FIGS. 3-5. Thus, upon receiving the desired pattern path, the logic block 116 changes relative disposition between the substrate and the beam in accordance with the prescribed path for cleaning the surface of the substrate.

From the block 116, the flow chart moves to the logic decision block 118 "Fire laser at current location?". If the laser has to be fired, i.e., the answer is "Yes", the logic moves to the block 120 "Admit controlled-energy laser pulse". At this instance, the motion/laser controller 53, as best shown in Figures 3-5, "commands" the laser 12 to generate a laser pulse which impinges at a predetermined area of the substrate 11 (in the "material removal" mode of operation for cleaning the substrate), or the material carrier element 14 (in the "material transfer" mode of operation). After the laser beam modifies either the deposition layer 15 of the material carrier element 14 or the surface of the substrate 11, the flow moves to the logic block 122 "Increment materials carrier position (deposition mode)". In this instance, the control unit 18 deactuates the laser 12, thus seizing the laser beam, and moves the material carrier element 14 to the next position according to the prescribed path 76 if the apparatus 10 operates in the "materials transfer" mode of operation.

If however the apparatus 10 operates in the "cleaning" mode of operation, the control unit 18 seizes the laser

beam and moves the substrate to the next position in accordance with the prescribed path 76. Thus, from the logic block 122, the flow chart returns to the logic block 116, where the translation of the substrate (or the laser beam) is performed along with prescribed path 76.

If however the answer to the decision logic block 118 is "No", meaning that the laser is not to be fired at a current location of the substrate or the laser beam, the logic flows to the block 124 "All Paths Complete?". If the answer is "Yes", the logic flows to the "End Procedure" block 126.

If however, in the logic block 124, if it is decided that not all prescribed paths have been yet completed, i.e., the answer is "No", the logic returns to the block 116 to translate the substrate (or the laser beam) along the prescribed path 76 for further leading the flow chart either along the loop comprised of logic blocks 118, 120, 122 and 116; or along the loop comprised of the logic blocks 118, 124, 116, in sequence.

A number of material compositions used in this invention are transparent to laser beams and such compositions, among others, may include fuse silica, borosilicate glass, polyester films such as Mylar, acrylic, as well as a wide variety of other compositions known in the art.

Although this invention has been described in

connection with specific forms and embodiments thereof, it will be appreciated that various modifications other than those discussed above may be resorted to without departing from the spirit or scope of the invention. For example, equivalent elements may be substituted for those specifically shown and described, certain features may be used independently of other features, and in certain cases, particular locations of elements may be reversed or interposed, all without departing from the spirit or scope of the invention as defined in the appended Claims.

WHAT IS CLAIMED IS:

1. A method for fabrication of miniature structures,
comprising the steps of:

providing a fabrication tool, including:

a substrate having a surface,

an energy beam directed towards said
substrate, and

control means operating said fabrication
tool in (1) material removal mode of operation and (2)
material transfer mode of operation, in a predetermined
sequence;

whereby when said fabrication tool is in said
material removal mode of operation, further providing a
direct access of said energy beam to said surface of said
substrate and cleaning said surface of said substrate by
changing a relative disposition between said energy beam
and said substrate in accordance with a first predetermined
pattern.

2. The method of Claim 1, further comprising the steps of:

providing a material carrier element having a deposition layer supported thereon and facing said substrate, whereby when said fabrication tool is in said material transfer mode of operation further including positioning said deposition layer in an interception path with said energy beam, and

changing a relative disposition between said energetic beam and said substrate in accordance with said first predetermined pattern, thereby transferring a deposition material contained in said deposition layer on said surface of said substrate at locations thereon cleaned during said material removal mode of operation.

3. The method of Claim 2, further comprising the steps of:

changing the mode of operation of said fabrication tool to a successive material removal mode of operation following said material transfer mode of operation, and

cleaning the surface of said substrate by changing relative disposition between said energy beam and said substrate in accordance with a second predetermined pattern.

4. The method of Claim 3, wherein said second predetermined pattern differs from said first predetermined pattern.

5. The method of Claim 3, wherein the surface of said substrate has said deposition material deposited thereon.

6. The method of Claim 1, wherein said energy beam includes a laser beam.

5 7. The method of Claim 6, wherein said laser beam includes an ultraviolet laser beam.

10 8. The method of Claim 2, further including the steps of:

displacing said material carrier element away from interception with said energy beam in said material removal mode of operation.

15 9. The method of Claim 2, further including the steps of:

20 maintaining said deposition layer in a position intercepting with said energy beam in said material transfer mode of operation.

10. The method of Claim 3, further including the steps of:

changing the relative disposition between said energetic beam and said substrate by controlling the position of said energy beam relative to said substrate.

11. The method of Claim 3, further including the steps of:

changing the relative disposition between said energy beam and said substrate by controlling the position of said substrate relative to said energy beam.

12. The method of Claim 3, further including the step of:

changing the relative disposition between said energetic beam and said substrate by controlling the positions of said energy beam and said substrate in coordinated fashion.

13. The method of Claim 3, in said "material removal" modes of operation, supplying a carrier gas flowing through said fabrication tool to remove residues formed as the result of said cleaning of said substrate surface.

14. The method of Claim 3, further including the steps of:

supplying an inert cover gas flowing through said fabrication tool to prevent areas of said substrate surface freshly exposed during said cleaning of said substrate surface from the re-oxidation.

15. The method of Claim 1, wherein said substrate surface includes at least one material to be removed therefrom, said method further comprising the step of:

adjusting, by means of said control means, intensity of said energy beam for removing said at least one material.

16. The method of Claim 1, wherein said substrate surface includes a plurality of different materials to be removed therefrom, said method further comprising the steps of:

adjusting, by means of said control means, intensity of said energy beam in accordance with positions of said materials to be removed from said substrate surface.

17. A method of patterned cleaning of a substrate surface, comprising the steps of:

providing a fabrication tool, including:

a substrate having a surface thereof,

an energy beam directed towards said

substrate, and

control means operating said fabrication

tool in either a material removal mode of operation and a

material transfer mode of operation whereby in said

material removal mode of operation further performing a

first cleaning of said substrate surface by allowing a

direct access for said energy beam to said substrate

surface and by changing a relative disposition between said

energy beam and said substrate in accordance with a first

predetermined pattern, and

performing a second cleaning of said

substrate surface by allowing a direct access for said

energetic beam to said substrate surface and by changing a

relative disposition between said energy beam and said

substrate in accordance with a second predetermined

pattern.

18. The method of Claim 17, further including the steps of:

providing a material carrier element having a deposition layer supported thereon and facing said substrate,

between said first and second cleaning steps, positioning said material carrier element into interception with said energy beam, thereby translating said fabrication tool into said material transfer mode of operation, and

changing relative disposition between said energetic beam and said substrate in accordance with said first predetermined pattern, thereby depositing a deposition material contained in said deposition layer onto said substrate surface at locations therein cleaned during said first cleaning.

19. The method of Claim 17, wherein said second cleaning is performed on said substrate surface including at least one deposited structure.

20. An apparatus for patterned cleaning of a substrate surface, comprising:

a substrate having a surface thereof,

an energy beam directed towards said substrate,

and

control means operating said apparatus in either a material removal mode of operation and material transfer mode of operation,

in said material removal mode of operation, said control means change the relative disposition between said energy beam and said substrate in accordance with a predetermined pattern, thus cleaning said substrate surface in a patterned fashion.

21. The apparatus of Claim 20, wherein said energy beam includes a laser beam.

5 22. The apparatus of Claim 21, wherein said laser beam includes a pulsed ultraviolet beam.

10 23. The apparatus of Claim 20, wherein said energy beam includes an electron beam.

15 24. The apparatus of Claim 20, wherein said energy beam includes an ion beam.

20 25. The apparatus of Claim 20, further including a material carrier element positionable in interception with said energy beam in said material transfer mode of operation and away from interception with said energetic beam in said material removal mode of operation, said material carrier element including a deposition layer supported thereon and facing said substrate.

25

26. The apparatus of Claim 20, wherein said control means further includes means for adjusting intensity of said energy beam in accordance with a type of material on said substrate surface.

27. The apparatus of Claim 21, wherein said substrate surface has a plurality of material disposed thereon, said adjusting means being adapted for adjusting the intensity of said energy beam in accordance with position of each of said plurality of materials.

28. The apparatus of Claim 20, further including means for supplying a carrier gas flowing through said apparatus for removing therefrom residues formed during said surface cleaning.

29. The apparatus of Claim 20, further including means for supplying an inert cover gas flowing through said apparatus for preventing reoxidation of areas on said substrate surface freshly exposed during said cleaning.

30. The apparatus of Claim 20, wherein said control means is operatively coupled to said energy beam to change the position thereof with respect to said substrate.

31. The apparatus of Claim 20, wherein said control means is operatively coupled to said substrate to change the position thereof with respect to said energy beam.

32. The apparatus of Claim 25, wherein said control means is operatively coupled to said material carrier element for changing the position thereof, thus setting said apparatus in one of said material removal and said material transfer modes of operation.

33. The apparatus of Claim 20, wherein said control means operates said apparatus in either of said material removal and material transfer modes of operation in a predetermined sequence.




FIG.1

2/7




FIG. 2B

1st CLEANING




FIG. 2A

2nd CLEANING





FIG. 2C

3/7

FIG. 3



4/7




FIG.4

5/7




FIG.5




FIG. 6

7/7




FIG.7

DECLARATION FOR PATENT APPLICATION

Docket Number (Optional)
MR2799-3

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled PATTERNED SURFACE CLEANING SYSTEM AND METHOD USED IN MINIATURE STRUCTURES MANUFACTURING PROCESSES the specification of which is attached hereto unless the following box is checked:

☐ was filed on _____ as United States Application Number or PCT International Application Number _____ and was amended on _____ (if applicable).

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to patentability as defined in 37 CFR §1.56.

I hereby claim foreign priority benefits under 35 U.S.C. § 119(a)-(d) or § 365(b) of any foreign application(s) for patent or inventor's certificate, or § 365(a) of any PCT International application which designated at least one country other than the United States, listed below and have also identified below, by checking the box, any foreign application for patent or inventor's certificate, or PCT International application having a filing date before that of the application on which priority is claimed.

Prior Foreign Application(s) Priority Not Claimed

_____ (Number)	_____ (Country)	_____ (Day/Month/Year Filed)	<input type="checkbox"/>
_____ (Number)	_____ (Country)	_____ (Day/Month/Year Filed)	<input type="checkbox"/>

I hereby claim the benefit under 35 U.S.C. § 119(e) of any United States provisional application(s) listed below.

60/135,488	24 May 1999
Application Number)	(Filing Date)

Application Number)	(Filing Date)
---------------------	---------------

I hereby claim the benefit under 35 U.S.C. § 120 of any United States application(s), or § 365(c) of any PCT International application designating the United States, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of 35 U.S.C. § 112.

I acknowledge the duty to disclose information which is material to patentability as defined in 37 CFR § 1.56 which became available between the filing date of the prior application and the national or PCT International filing date of this application.

PCT/US00/09816	24 May 2000	Pending
Application Number)	(Filing Date)	(Status-patented, pending, abandoned)

Application Number)	(Filing Date)	(Status-patented, pending, abandoned)
---------------------	---------------	---------------------------------------

I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith:

Address all telephone calls to
Address all correspondence to

MORTON J. ROSENBERG, ESQ., REG. # 26,049;
DAVID I. KLEIN, ESQ., REG. # 33,253; JUN Y. LEE, ESQ., REG. # 40,262
MORTON J. ROSENBERG at telephone number 410-465-6678
ROSENBERG, KLEIN & LEE
3458 ELLICOTT CENTER DRIVE-SUITE 101
ELLICOTT CITY, MD 21043
FAX #: 410-461-3067
E-MAIL ADDRESS: rkl@rklatlaw.com

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the same so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Full name of sole or first inventor (given name, family name) Michael T. Duignan (Duignan is Family Name)

Inventor's signature Michael T. Duignan Date 12 Jan 2001

Residence Same as Post Office Address Citizenship US

Post Office Address 1520 R Street, N.W.

Washington, D.C. 20009 DC

Full name of second joint inventor, if any (given name, family name) _____

Second Inventor's signature _____ Date _____

Residence _____ Citizenship _____

Post Office Address _____

☐ Additional Inventors are being named on separately numbered sheets attached hereto.